

XIAMETER[®] brand Sealant Formulation Materials

Product Technical Data/Selection Guide (North America)

Make the XIAMETER[®] brand your one-stop shop for the materials you need to formulate your sealants.

Polymers							
Product Name	Description	Viscosity	Shelf Life	Silanol Content	Specific Gravity @ 25°C	Packaging	Material #
XIAMETER [®] OHX-4010 Polymer, 4,000 cs	Polydimethylsiloxane polymer with terminated, curable silanol functionality	4,000 cs	1,800 days	0.13%	0.975	200 kg drum	4022439
XIAMETER [®] OHX-4012 Polymer, 6,000 cs	OH end-blocked polydimethylsiloxane	6,000 cs	1,800 days	0.13%	0.97	200 kg drum/ 1,000 kg IBC	4027605/ 4027604
XIAMETER [®] OHX-4020 Polymer, 12,500 cs	—	12,500 cs	—	—	—	—	—
XIAMETER [®] OHX-4050 Polymer, 16,500 cs	Polydimethylsiloxane polymer with terminated, curable silanol functionality	16,500 cs	1,800 days	0.075	0.975	200 kg drum/ 1,000 kg IBC	4022623/ 4022668
XIAMETER [®] OHX-4070 Polymer, 50,000 cs	100% water-clear silicone fluid polymer; can be used as an intermediate for silicone-based sealant manufacturing; essentially odorless	50,000 cs	1,800 days	0.04	0.98	900 kg IBC	4025561
XIAMETER [®] OHX-4080 Polymer, 80,000 cs	100% water-clear silicone polymer; can be used as an intermediate for silicone-based sealant manufacturing; essentially odorless	80,000 cs	1,800 days	—	0.975	200 kg drum/ 1,000 kg IBC	4028082/ 4026010

Fluids and Cyclics							
Product Name	Description	Viscosity	Shelf Life	Flash Point, Closed Cup	Specific Gravity @ 25°C	Packaging	Material #
XIAMETER [®] PMX-200 Silicone Fluid, 100 cs	100% active polydimethylsiloxane polymer	100 cs	1,080 days	>100°C	0.96	200 kg drum	4088892
XIAMETER [®] PMX-200 Silicone Fluid, 1,000 cs	100% active polydimethylsiloxane polymer	1,000 cs	1,080 days	>100°C	0.971	200 kg drum	4088895

Silanes							
Product Name	Description	Viscosity	Shelf Life	Flash Point, Closed Cup	Specific Gravity @ 25°C	Packaging	Material #
XIAMETER [®] OFS-1579 Silane	Acetoxy silane used as a crosslinker for acetoxy-cure silicone RTV sealants	—	720 days	—	—	220 kg drum/ 1,130 kg IBC	4022740/ 4022739
XIAMETER [®] OFS-6020 Silane	Aminoethylaminopropyltrimethoxysilane – H ₂ NC ₂ H ₄ NHC ₃ H ₆ -Si(OCH ₃) ₃ coupling agent for many thermoset and thermo-plastic resins with glass or mineral fillers	5 cs	1,080 days	85°C	1.03	205 kg drum/ 1,025 kg IBC	4022790/ 4022789
XIAMETER [®] OFS-6070 Silane	Methyltrimethoxysilane – CH ₃ -Si(OCH ₃) ₃	—	1,080 days	8°C	0.95	180 kg drum/ tanker	4022792/ 4022791

SAFE HANDLING INFORMATION

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE XIAMETER WEBSITE AT WWW.XIAMETER.COM, OR FROM YOUR XIAMETER REPRESENTATIVE OR DISTRIBUTOR, OR BY CALLING YOUR GLOBAL XIAMETER CONNECTION.

LEARN MORE

Visit www.xiameter.com to learn more about the many product options available to you from the XIAMETER brand.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Dow Corning is a registered trademark of Dow Corning Corporation.

XIAMETER is a registered trademark of Dow Corning Corporation.

©2010 Dow Corning Corporation. All rights reserved.

Printed in USA AGP10950 Form No. ___-___01



**AUTHORIZED DISTRIBUTOR
1-800-448-0406**

